



Packing 50 gm.

# J01

# JARI (SPARKLE)

For Sparkling epoxy grout (Silver, Copper, Gold, Red)

#### DESCRIPTION :

JARI (SPARKLE) are specially designed to get special glitter effect and enhance the beauty of tiling. It should be mixed with epoxy tile grout to get sparkling.

#### FEATURES AND ADVANTAGES

- Easy to use - just mix with T02 SOLPOXY epoxy grout on site, ready to use.
- Suitable for variety of tile and stones - Ceramic, vitrified, marbles, granites etc.
- Gives Sparkling & Shining tile joints.
- Available in four variants (Silver, Copper, Gold, Red).
- Excellent chemical resistance.

#### PRECAUTIONS & NOTE

- Do not apply on wet/damp tile joints. Always apply on completely dry tile joints.
- Do not over-mix the material. Over-mixing can reduce the pot life.
- While cleaning change frequently the water. Change cleaning cloth/ sponge when they are impregnated with grout.
- Do not allow water to flow/run into un-grouted joints while application.
- Protect from direct rainfall/ foot traffic for at least 24 hours.

#### GUIDELINE FOR USAGE

- Shake the bottle of Hardener and stir the Resin prior to mixing.
- Pour Part A (Resin) & Part B (Hardener) into a clean mixing pail.
- Mix thoroughly by hand or with a slow speed mixer (<300 RPM) until liquids are completely blended.
- Add slowly the Filler part, mixing thoroughly until all of the Filler is dispersed
- Then add the sparkles part till a uniform colour and lumps-free consistency is achieved.
- Avoid entraining air by mixing at very high speed or by over-mixing.
- Ideally use the paste within 45 minutes from mixing.

#### SHELF LIFE & STORAGE

36 months for sealed pack when stored under cover, out of direct sunlight, dampproof condition and protect from extremes of temperature (store between +15°C to +35°C temperature).

#### HEALTH & SAFETY PRECAUTIONS

- Wear suitable protective clothing, gloves, goggles, nose mask during application.
- In case of contact with skin & eyes, rinse immediately with plenty of clean water & seek medical advice.
- Keep out of reach of children.

# TECHNICAL INFORMATION

## PRODUCT DETAIL J01-JARI (SPARKLE)

Sr.	Testing Properties	Test Result
1	Available Color	Silver, Copper, Gold, Red
2	Density	1.5 g/ cc
3	Size	Approx. 0.2 mm
4	Water Solubility	Insoluble in Water
5	Melting Point	≥ 170°C
6	Tentative Mixing Ratio (T02 SOLPOXY Epoxy: Sparkles)	50 gm in 1 kg RTM 3 – 7% of weight of RTM Epoxy

## APPLICATION PROPERTIES T02-SOLPOXY EPOXY + J01-JARI(SPARKLE)

Sr.	Testing Properties	Test Result
1	Mixed Density	1.75 ± 0.05 Kg/ litre
2	Pot life @ 30°C	Approx. 60 minutes
3	Joint Width	2 – 15 mm
4	Sag Resistant	No sag
5	Application Temperature	from +10°C to +35°C
6	Light Foot Traffic	24 hours
7	Regular Traffic	72 hours

**Note:** Test results are indicative as per testing method specified in standard. Test results may vary as per substrate, site condition & testing machine etc. Actual field performance will depend on installation methods and site conditions.



Plot No. 32, Shraddha Industrial Estate-2,  
Near Cefone Ceramic, At. Pipli Village,  
Morbi-363 642 (Gujarat) INDIA.



[www.solcon.co.in](http://www.solcon.co.in)



[kmk@solcon.co.in](mailto:kmk@solcon.co.in)



+91 90818 19280